

CLASSIC LINE SUCUPIRA

Geometric characteristics (according to EN 13227)

Thickness	9mm
Width	80 to 180 mm
Length	1000 to 2200mm
Tolerance in thickness	+/- 0,2mm
Tolerance in width	+/- 0,2mm
Moisture content	Between 7% and 11%
Weight	+/- 7kg/sqm
Packaging	per 10 pcs
Bevel	With or without bevel/ u-bevel

Specification wood species

Wood species	Sucupira
Botanical name	Diplotropis purpurea
Area of growth	South America
Classification	Brown to dark brown
Sound sapwood	Not permitted
Sound and intergrown knots (1)	Ø max 10mm
Unsound knots (1)	Not permitted
Surface checks	Not permitted
Bark pocket	Not permitted
Lightning shake	Not permitted
Colour variation	Permitted
Slope of grain and medullary ray	Permitted
Bio deterioration	Not permitted
Saw cut	Free

(1) Measurement method for knots according to EN 1310